



# 福建省安源（安泰）橡胶科技有限公司

## Antishrinking Agent A-008 Technical Data System

Active ingredients	Quinoline derivatives	Other ingredients	Adsorbents, rubber
--------------------	-----------------------	-------------------	--------------------

### Product introduction

This antioxidant is suitable for natural rubber/NBR/SBR/EP(D)M/CR and various synthetic rubbers. It has excellent protection against aging phenomena caused by heat and oxygen. Used in combination with other types of antioxidants or antioxidants, it has better protection against flexural aging. It is a commonly used antioxidant in the manufacture of rubber products such as rubber shoes/hoses/tires/tapes/wire protectors. It has large solubility in rubber, and will not be spit out if the dosage is more than 6phr, but due to its natural color, attention should be paid to the relocation of color in case of large dosage.
--

### Product index

Items	appearance	density	ash content	moisture content	ML(1+4)50°C
Unit	——	g/cm <sup>3</sup>	%	%	——
Index	Brown flaky granules	1.20	≤30	≤1	inapplicable

### Usage method

Rubber plasticizing stage can be put into, according to the general rubber antioxidant use
This antioxidant can be used alone or in combination with other antioxidants such as MB or BHT/1076.
Suggested dosage: 1.0phr-4.0phr, please increase or decrease as your needs.

### Package specification/ shelf life

Bag/box lined with plastic bags, 25kg/ bag (box)
12 months from the date of production. If the storage is expired, it can still be used after re inspection

### Attention points

1. This product is not flammable but combustible, use should be careful to keep away from fire	<b>Flammability</b>       <b>negative</b>
2. The storage temperature and the number of layers should not be too high to prevent the granules from softening and agglomeration	
3. Keep away from strong acids, strong alkalis and strong oxidizers to avoid product failure.	

公司名称	福建省安源橡胶科技有限公司		
地址	福建省石狮市蚶江镇洪窟九龙山工业区22号		
电话	0595-85151198	网址	<a href="http://www.fjayxj.com">www.fjayxj.com</a>